



H.P. White Laboratory, Inc.

BALLISTIC RESISTANCE TEST

Client : 7296: VETERANS MFG, L.L.C.

Job No. : 000009056 Test Date : 2/11/19

TEST PANEL

Manufacturer : VETERANS MFG, L.L.C.
 Size : ADULT UNIVERSAL
 Thicknesses : NA
 Avg. Thick. : NA
 Description : PROPRIETARY
 BLUE PFD

Sample No. : SAMPLE 2 (FRONT)
 Weight : 2.94 lbs.
 Hardness : NA
 Plies/Laminates : NA

Date Rec'd. : 1/18/19
 Via :
 Returned :

SET-UP

Shot Spacing : NIJ-STD-0101.06
 Witness Panel : NA
 Obliquity : 0, 30, & 45 deg.
 Backing Material : 5.5" CLAY/PLYWOOD
 Conditioning : SUBMERGED

Primary Vel. Screens : 6.5 ft., 11.5 ft.
 Primary Vel. Location : 9.0 ft. From Muzzle
 Residual Vel. Screens : NA
 Residual Vel. Location : NA
 Range to Target : 17.3 ft.
 Target to Wit. : 0.0 in.

Range No. : 2
 Temp. : 69 F
 BP : 30.31 in. Hg
 RH : 36%
 Barrel No./Gun : .357 SIG R2
 Gunner : MILLER
 Recorder : STREETT

AMMUNITION

(1) : .357 SIG FMJ FN, 125 gr.
 (2) :
 (3) :
 (4) :

Lot No. : SPEER 4362, M30W
 Lot No. :
 Lot No. :
 Lot No. :

APPLICABLE STANDARDS OR PROCEDURES

- (1) : NIJ-STD-0101.06 LEVEL IIIA (MODIFIED)
- (2) : PRE TEST CLAY DROPS: 19mm, 20mm, 20mm, 18mm, 19mm
- (3) : PRE TEST CLAY TEMP: 99.8 °F

Shot No.	Ammo.	Time 1 (usec)	Velocity 1 (ft/s)	Time 2 (usec)	Velocity 2 (ft/s)	Avg. Vel. (ft/s)	Penetration	Footnotes
1	1	3403	1469	3403	1469	1469	None	DEF. 9mm
2	1	3409	1467	3408	1467	1467	None	DEF. 10mm
3	1	3365	1486	3365	1486	1486	None	DEF. 9mm
4	1	3385	1477	3385	1477	1477	None	(b)
5	1	3415	1464	3414	1465	1464	None	(a)
6	1	3450	1449	3450	1449	1449	None	

REMARKS :

FOOTNOTES :

- (a) SHOT IMPACTED AT A 30° ANGLE.
- (b) SHOT IMPACTED AT A 45° ANGLE.